

5 WHAT IS CLAIMED IS:

1. A thermodynamically stable material comprising:

(A) a cross-linked siloxane comprising:

alkoxysilyl functionality, $-X-SiR^4_n(OR^5)_{3-n}$, and

cross-links, $-E^1-Y-E^2-$, with each end of such cross-links bonded to a silicon,

wherein,

X is a divalent group that is a hydrocarbon, a siloxane or some combination of these,

R^4 and R^5 are independently monovalent hydrocarbon groups,

E^1 and E^2 are independently $-CH_2CH_2-$ or $-CH=CH-$,

Y is a divalent group that is a hydrocarbon, a siloxane or some combination of these and
n is 0 to 2;

and

(B) a diluent.

SUB
A2
10060713-013002
20061013-013002

- 5 2. The material of claim 1 wherein:
 (A) is a cross-linked siloxane comprising:

alkoxysilyl functionality, $-X-SiR_n^4(OR^5)_{3-n}$, and

cross-links, $-E^1-Y-E^2-$, with each end of such cross-links bonded to a silicon,

10

wherein,

SUB X is a divalent hydrocarbon group having from 2 to 12 carbons,

27 R⁴ and R⁵ are independently monovalent hydrocarbon groups having from 1 to 30 carbons,


E¹ and E² are $-CH_2CH_2-$,

Y is a divalent hydrocarbon group having from 1 to 30 carbons or a siloxane and
 n is 0 to 2.

15 20060713.01300

3. The material of claim 1 wherein:

(A) is a cross-linked alkoxyfunctional siloxane of average formula:



where,

R^1 is a monovalent hydrocarbon group;


R^2 is $-(\text{CH}_2)_d\text{SiR}^4_n(\text{OR}^5)_{3-n}$;

R^3 is $-\text{E}^1\text{-Y-E}^2\text{-R}^9$ or a siloxane containing $-\text{E}^1\text{-Y-E}^2\text{-R}^9$ with E^1 in this last mentioned siloxane bonded to silicon as well as to Y,

R^4 and R^5 are independently monovalent hydrocarbon groups;

E^1 and E^2 are independently $-\text{CH}_2\text{CH}_2-$ or $-\text{CH}=\text{CH}-$;

Y is a divalent group that is a hydrocarbon, a siloxane or some combination of these;



a is 0 – 100,000,000;

b is 1 – 50,000,000;

c is 1 – 10,000,000;

$4 \leq \text{cc} \leq 2\text{c}+2$;

d is 2 – 12;

n is 0 – 2.

SUB 10060713-013002

5 4. The material of claim 3 where,

in (A):

R^1 is a monovalent hydrocarbon group having 1 to 12 carbons,

R^3 is $-E^1-Y-E^2-R^9$,

10 R^4 is a monovalent hydrocarbon group having 1 to 12 carbons,

R^5 is methyl, ethyl, isopropyl, phenyl or benzyl,

E^1 and E^2 are $-\text{CH}_2\text{CH}_2-$, and

Y is a divalent hydrocarbon group having from 1 to 30 carbons; and


15 (B) is a siloxane other than that chosen for (A) or a mixture of siloxanes not containing that chosen for (A).

5. The material of claim 3 where the weight ratio of (A):(B) is from 1:100 to 10:1.

20 6. The material of claim 3 where in (A),

R^3 is $-E^1-Y-E^2-R^9$,

Y is



R^{10} is a monovalent hydrocarbon group and

p is 0 to 20,000.

7. The material of claim 6 where

in (A):

R^1 is methyl,

35 R^4 and R^5 are independently monovalent hydrocarbon groups having from 1 to 30 carbons,


E^1 and E^2 are $-\text{CH}_2\text{CH}_2-$ and

R^{10} is methyl.

SUB 27 10050713-013002

8. The material of claim 1 wherein

(A) is a cross-linked alkoxysilyl functional siloxane of average formula:



where,

R¹¹ is a monovalent hydrocarbon group;

R⁴² is a monovalent hydrocarbon group or $-(\text{CH}_2)_d\text{SiR}^4_n(\text{OR}^5)_{3-n}$, with the proviso that

R⁴² is at least in part $-(\text{CH}_2)_d\text{SiR}^4_n(\text{OR}^5)_{3-n}$;

R¹³ is $-\text{E}^1\text{-R}^{16}\text{-Y-R}^{17}\text{-E}^2\text{-R}^{19}$, or a siloxane containing $-\text{E}^1\text{-R}^{16}\text{-Y-R}^{17}\text{-E}^2\text{-R}^{19}$ with E¹ in this last mentioned siloxane bonded to silicon and R¹⁶;

Q is on average at least 80 mole percent (SiO₂) with the balance made up of one or more other types of siloxane units;


R⁴ and R⁵ are independently monovalent hydrocarbon groups;

E¹ and E² are independently $-\text{CH}_2\text{CH}_2-$ or $-\text{CH}=\text{CH}-$;

R¹⁶ and R¹⁷ are independently divalent hydrocarbon groups or nullities;

Y is a divalent group that is a hydrocarbon, a siloxane or a combination of these

R¹⁹ is



j is 1 to 100;

q is 1 to 500,000;

r is 1 to 1,000,000;

t is 1 to 100,000;

d is 2 to 12; and

n is 0 to 2, with the proviso that

q+t : r is 0.5 to 4.0.

SUB
C27

10060713-013002

5 9. The material of claim 8 where in (A):


R¹¹ is a monovalent hydrocarbon group having from 1 to 40 carbons;

R¹³ is -E¹-R¹⁶-Y-R¹⁷-E²-R¹⁹;

R⁴ and R⁵ are independently monovalent hydrocarbon groups having from 1 to 30 carbons;

10 R¹⁶ and R¹⁷ are independently divalent hydrocarbons groups having from 1 to 8 carbons or a nullity;

Y is



R²⁰ is a monovalent hydrocarbon group having from 1 to 40 carbons; and


v is 0 to 20,000.

SUB
A2

10060743-013002
200510-013002

5 10. The material of claim 1 wherein;

(A) is a cross-linked alkoxysilyl functional siloxane comprising subunits of formula:



15 where,

R^1 is a monovalent hydrocarbon group;


R^2 is $-(\text{CH}_2)_d\text{SiR}^4_n(\text{OR}^5)_{3-n}$;

R^3 is $-\text{E}^1\text{-Y-E}^2\text{-R}^9$ or a siloxane containing $-\text{E}^1\text{-Y-E}^2\text{-R}^9$ with E^1 in this last mentioned siloxane bonded to silicon as well as to Y,

20 R^4 and R^5 are independently monovalent hydrocarbon groups;

E^1 and E^2 are independently $-\text{CH}_2\text{CH}_2-$ or $-\text{CH}=\text{CH}-$;

Y is a divalent group that is a hydrocarbon, a siloxane or some combination of these;



a is 0 - 1,000;

30 b is 1 - 500;

c is 1 - 100;


$4 \leq \text{cc} \leq 2\text{c}+2$;

d is 2 - 12;

n is 0 - 2.

35

- 5 11. The material of claim 1 wherein
 (A) is a cross-linked alkoxyisilyl functional siloxane comprising subunits of formula:



SUB
 15 27
 where,

R¹¹ is a monovalent hydrocarbon group;

R⁴² is a monovalent hydrocarbon group or $-(\text{CH}_2)_d\text{SiR}^4_n(\text{OR}^5)_{3-n}$, with the proviso that

R⁴² is at least in part $-(\text{CH}_2)_d\text{SiR}^4_n(\text{OR}^5)_{3-n}$;

R¹³ is $-\text{E}^1\text{-R}^{16}\text{-Y-R}^{17}\text{-E}^2\text{-R}^{19}$, or a siloxane containing $-\text{E}^1\text{-R}^{16}\text{-Y-R}^{17}\text{-E}^2\text{-R}^{19}$ with E¹ in this last mentioned siloxane bonded to silicon and R¹⁶;

Q is on average at least 80 mole percent (SiO₂) with the balance made up of one or more other types of siloxane units;


R⁴ and R⁵ are independently monovalent hydrocarbon groups;

E¹ and E² are independently $-\text{CH}_2\text{CH}_2-$ or $-\text{CH}=\text{CH}-$;

R¹⁶ and R¹⁷ are independently divalent hydrocarbon groups or nullities;

Y is a divalent group that is a hydrocarbon, a siloxane or a combination of these

R¹⁹ is



j is 1 to 100;

q is 1 to 500;

r is 1 to 1000;

t is 1 to 100;

d is 2 to 12; and

n is 0 to 2, with the proviso that

q+t : r is 0.5 to 4.0.

5 12. A method of making a thermodynamically stable material, the method comprising cross-linking, in the presence of a hydrosilylation catalyst,

- (1) an $\equiv\text{SiH}$ functional siloxane and,
 (2) an alpha, omega diene, diyne or ene-yne.

10 with the provisos

54B
627 that at least one of (1) and (2) has alkoxysilyl functionality, $-\text{X}-\text{SiR}^4_n(\text{OR}^5)_{3-n}$,

where,

X is a divalent group that is a hydrocarbon a siloxane or some combination of these,

15 R^4 and R^5 are independently monovalent hydrocarbon groups and

n is 0 to 2,

that (1) and (2) are dispersed in a diluent, and

that the weight ratio of (1)+(2)+ the product of the cross-linking of (1) and (2):diluent is
 1:100 to 10:1.

20

10060713-013002

13. The method of claim 12 wherein

(1) is an $\equiv\text{SiH}$ functional siloxane having alkoxyethyl functionality of the form,




X is a divalent group that is a hydrocarbon, a siloxane or some combination of these,

R^4 and R^5 are independently monovalent hydrocarbon groups and

n is 0 to 2.

14. The method of claim 13 where,

(1) is an alkoxyethyl functional siloxane of average formula:



where,

R^1 is a monovalent hydrocarbon group;

R^2 is $-(\text{CH}_2)_d\text{SiR}^4_n(\text{OR}^5)_{3-n}$;

R^4 and R^5 are independently monovalent hydrocarbon groups;

a is 0 - 1,000;

b is 1 - 500;

c is 1 - 100;

$2 \leq \text{cc} \leq 2c+2$;

d is 2 - 12; and

n is 0 - 2;


(2) is $\text{E}^3\text{-Y-E}^4$ or a siloxane containing $\text{E}^3\text{-Y-E}^4$, where

E^3 and E^4 are independently $\text{CH}_2=\text{CH-}$ or $\text{CH}\equiv\text{C-}$; and

Y is a multivalent group that is a hydrocarbon, a siloxane or some combination of these.

SUB 227 10060713-013002

5 15. The method of claim 13, wherein,
(1) is on average



10

R^2 is $-(\text{CH}_2)_p\text{SiR}^4_n(\text{OR}^5)_{3-n}$;

R^4 and R^5 are independently monovalent hydrocarbon groups;

i is 0 to 2;

u is 0 to 2;

$i+u+m = 2$;

c is 0 to 20,000;

d is 0 to 2000;

$u+d \geq 2$;

k is 0 to 2000;

m is 0 to 2;


$k+m \geq 1$;

p is 2 to 12;

n is 0 to 2; and

25

(2) is on average



e is 0 to 2;

f is 0 to 2;

$e+f = 2$;

g is 0 to 20,000;


h is 0 to 1000; and

$e+h \geq 2$

30

SUB
627
10060713-013002
2006-10-13

- 5 16. The method of claim 13, wherein,
 (1) is on average



where,

15 R^{11} is a monovalent hydrocarbon group;

R^{42} is a monovalent hydrocarbon group or $-(\text{CH}_2)_d\text{SiR}^4_n(\text{OR}^5)_{3-n}$, with the proviso that

R^{42} is at least in part $-(\text{CH}_2)_d\text{SiR}^4_n(\text{OR}^5)_{3-n}$;

Q is on average at least 80 mole percent (SiO_2) with the balance made up of one or more other types of siloxane units;

20 R^4 and R^5 are independently monovalent hydrocarbon groups;

j is 1 to 100;

q is 1 to 500;

r is 1 to 1000;


25 t is 1 to 100;

d is 2 to 12;

n is 0 to 2;

q+t : r is 0.5 to 4.; and

30 (2) is on average



5 where x is 0 to 20,000,

y is 0 to 2000,

z is 0 to 2,

$2 \leq z+y \leq 2000$,

R²¹ is a monovalent terminally aliphatic unsaturated hydrocarbon having from two to twelve carbons, and

R²² is a monovalent hydrocarbon having one to forty carbons.

SUB
C27
10

20061013 01:3002

5 17. The method of claim 12, wherein

(1) is an $\equiv\text{Si-H}$ functional polyorganosiloxane and

(2) is a polyorganosiloxane resin having alpha-omega diene, diyne or ene-yne functionality.

10 18. The method of claim 17 wherein at least 80 mole percent of subunits in the polyorganosiloxane resin of (2) are (SiO_2) and $((\text{R}^i)_3\text{SiO}_{0.5})$, where R^i is a monovalent hydrocarbon group, the ratio in (2) of siloxane units other than SiO_2 to SiO_2 units there is 0.5 to 4.0, and X in the alkoxysilyl functionality is a hydrocarbon.

15 19. A material preparable by the method of claim 12.

20 20. The product of the method of claim 12.

21. The product of the method of claim 13.

22. The product of the method of claim 14.

23. The product of the method of claim 15.

25 24. The product of the method of claim 16.

25. The product of the method of claim 17.

26. The product of the method of claim 18.

30 27. A material, comprising the composition of claim 1, that is a personal care product.

28. The material of claim 27 that is a hair, skin or underarm care product.

35 29. The material of claim 28 that is a conditioner, moisturizer, body wash, cosmetic foundation, blush, lipstick, eye liner, mascara, eye shadow, antiperspirant or deodorant.

sub
a27
10060713
013000